Paper 46



©Civil-Comp Press, 2012 Proceedings of the Eleventh International Conference on Computational Structures Technology, B.H.V. Topping, (Editor), Civil-Comp Press, Stirlingshire, Scotland

Numerical Analysis of the Initiation of Delamination in Fibre Composites

J.-W. Simon and S. Reese Institute of Applied Mechanics RWTH Aachen University, Germany

Abstract

Since delamination is a major failure mode of layered composites, predicting its initiation is essential for the design of composite structures. Evaluating delamination onset criteria based on stress-strength relations requires an accurate representation of the through-the-thickness stress distribution, which is delicate for thin shell-like structures. Therefore, in this paper, a solid-shell finite element is utilized, which allows for incorporating a fully three-dimensional, anisotropic, micro-mechanically motivated material model, still being suited for application to thin structures. Moreover, locking phenomena are cured by using both the EAS and the ANS concept, and numerical efficiency is ensured through reduced integration.

Keywords: fibre-reinforced composite, layered composite, delamination, solid-shell concept, enhanced strain formulation, reduced integration.

1 Introduction

Fibre-reinforced composites are gaining more and more importance in technical applications. Their most beneficial characteristics, the very high Young's modulus and low density, are particularly leveraged in shell-like structures of lightweight constructions. The composites examined in this paper consist of multiple layers, each of which is composed of a woven fabric, with two families of fibres, embedded in a matrix material. Besides this anisotropic structure, the stress-strain behaviour of fibre composite materials is highly non-linear. Moreover, the response of the materials in tension and compression can differ significantly.

The majority of models accounting for anisotropic material behaviour at finite strains were developed in the field of biomechanics. For instance, axisymmetric orthotropic blood vessels were investigated in [1], whereas biological soft tissues were

modeled in [2] on the basis of an incompressible transversely isotropic law for moderate deformations. A description of the transversely isotropic behaviour of rubber was presented in [3], and orthotropic constitutive equations were provided in [4] for the simulation of human leg impact problems. More recently, anisotropic material models were proposed incorporating the micro-mechanical structure of wood, e.g. [5, 6]. In the present paper, however, the model proposed by Reese in [7] for fibre-reinforced rubber-like composites was adopted, in which the transition from the micro-scale to the macro-scale is formulated in a general manner. Therefore, this model is not restricted to rubber-like materials but also suitable for the carbon fibre-reinforced plastics (CFRP) considered here.

Structural collapse in fibre composite structures is caused by the evolution of either matrix transverse cracking, fibre fracture, or delamination. From these different damage modes, the delamination is particularly important, because it drastically reduces the bending stiffness of the structure and promotes local buckling in case of compressive loads. Including delamination into the computation of composite structures requires the definition of an appropriate criterion for its onset as well as the prediction of its growth after an initial crack has evolved.

For the initiation of delamination, different criteria exist, formulated in dependence of stress-resistance relations, e.g. [8–12]. After onset of delamination, the high stress gradients appearing at the crack front prohibit employing solely stress-based criteria. Thus, fracture mechanics approaches are often used for simulating the delamination propagation, such as the virtual crack closure technique, [13–17]. As an alternative, delamination growth can be treated within the framework of damage mechanics using cohesive zone models, which are incorporated into the finite element simulation by interface elements, e.g. [18–21]. However, in this paper, the onset of delamination is addressed based on stress-resistance relations.

Since fibre-reinforced composites are mostly applied in thin shell-like structures, the element formulation demands providing a suitable shape for thin structures while displaying realistically the three-dimensional stress states. Although shell formulations exist, which take into account the through-the-thickness stretching, see e.g. [22–24], the implementation of three-dimensional material models is much simpler in the context of solid elements. On the other hand, the latter typically provide a poor performance when being applied to thin shell-like structures. In particular, there are different locking phenomena to be coped with, which cause an overestimation of the stress state and an underestimation of the deformation. Using solid-shell elements represents one strategy to overcome this problem by combining the advantages of both solid elements and shell elements at the same time. Further, applying the enhanced assumed strain (EAS) concept eliminates the volumetric locking in case of (nearly) incompressible materials as well as the Poisson thickness locking, which occurs in bending problems of shell-like structures due to the non-constant distribution of transverse normal strain over the thickness.

In literature, one can find several solid-shell formulations incorporating the EAS concept, see e.g. [25–27], to name only a few. To cure the transverse shear lock-

ing, which is present in standard eight-node hexahedral elements, the assumed natural strain (ANS) method is applied. In the context of full integration formulations, the ANS can be found e.g. in [28–30], and for reduced integration solid-shell formulations e.g. in [31–34]. The formulation presented in this paper is based on the works of Schwarze and Reese [32–34].

For laminated layered composites, the accurate determination of the through-thethickness stress distribution was recently investigated by several authors. For instance, in [35] an improved shell formulation was used for this, whereas in [36] and [37] the investigations were based on the solid-shell concept. For a more elaborate literature overview, the reader is referred to the review papers [38–40] and the references therein.

However, to our knowledge no solid-shell formulations exist, which consider the orthotropic behaviour of fibre composites with woven fabric accounting for different fibre directions.

2 Orthotropic material model

The fibre composites examined in this paper consist of stacked layers, each of which is composed of a woven fabric embedded in a matrix material. The anisotropic material behaviour of such composites is taken into account by using the micro-mechanically motivated model proposed in [7]. Describing the matrix by the Neo-Hooke material model allows for incorporating rubber-like matrix materials with sufficient accuracy, whereas viscous effects of e.g. epoxy resin cannot be represented. However, in the following, the basics of the continuum model are summarized. Therein, parameters are chosen to represent approximately the behaviour of carbon fibres in an epoxy resin matrix.

2.1 Concept of structural tensors

Introducing the deformation gradient **F**, the deformation of a continuous body is represented by the right Cauchy-Green tensor

$$\mathbf{C} = \mathbf{F}^{\mathrm{T}} \mathbf{F} \tag{1}$$

The characterization of a hyperelastic body is then given by the existence of a scalar potential, which is the stored energy function $W = W(\mathbf{C})$, such that

$$\mathbf{S} = 2 \, \frac{\partial \mathbf{W}(\mathbf{C})}{\partial \mathbf{C}} \tag{2}$$

is the second Piola-Kirchhoff stress tensor. In the case of orthotropic material behaviour, the energy function $W(\mathbf{C})$ reduces to an isotropic function of \mathbf{C} and the structural tensors \mathbf{M}_1 and \mathbf{M}_2 , which are defined by

$$\mathbf{M}_1 = \boldsymbol{n}_1 \otimes \boldsymbol{n}_1$$
 and $\mathbf{M}_2 = \boldsymbol{n}_2 \otimes \boldsymbol{n}_2$ (3)

where the vectors n_1 and n_2 are oriented in parallel direction to the fibres. For a discussion of the theoretical background, the reader is referred to [41] and the references therein. Then, the strain energy function W can be represented in dependence of the following invariants:

$$I_1 = \operatorname{tr} \mathbf{C} \qquad \qquad I_2 = \frac{1}{2} \left[\left(\operatorname{tr} \mathbf{C} \right)^2 - \operatorname{tr} \left(\mathbf{C}^2 \right) \right] \qquad \qquad I_3 = \det \mathbf{C} \qquad (4a)$$

$$I_4 = \operatorname{tr}\left(\mathbf{C} \cdot \mathbf{M}_1\right) \qquad I_5 = \operatorname{tr}\left(\mathbf{C}^2 \cdot \mathbf{M}_1\right) \tag{4b}$$

$$I_6 = \operatorname{tr}\left(\mathbf{C} \cdot \mathbf{M}_2\right) \qquad I_7 = \operatorname{tr}\left(\mathbf{C}^2 \cdot \mathbf{M}_2\right) \tag{4c}$$

2.2 Strain energy function

In this work, the anisotropic model from Reese [7] is adopted, which assumes that the fibres do not carry any load in case of compression but only in tension, which is not realistic for the CFRP considered here. Therefore, this model is slightly modified, such that the matrix acts as an elastic continuous support for the embedded fibres. Moreover, the fibre volume fractions $0 \le \varphi_1$ and $0 \le \varphi_2$ for the two families of fibres are introduced, where $\varphi_1 + \varphi_2 \le 1$ holds. Except of this, we adopt the mentioned model and use the following strain energy function:

$$W = (1 - \varphi_1 - \varphi_2) W_{NH}(I_1, I_3) + W_{ani}(\varphi_1, \varphi_2, I_1, I_2, I_4, I_5, I_6, I_7)$$
(5)

Here, W_{NH} denotes the Neo-Hookean part displaying the isotropic case in the small strain regime. The strain energy function is given by

$$W_{NH}(I_1, I_3) = \frac{\mu}{2} \left(I_1 - 3 \right) - \mu \ln \sqrt{I_3} + \frac{\Lambda}{4} \left(I_3 - 1 - 2 \ln \sqrt{I_3} \right) \tag{6}$$

The anisotropic behaviour of the fabric is introduced by the part

$$W_{ani}(\varphi_1, \varphi_2, I_1, I_2, I_4, I_5, I_6, I_7) = K_1^{iso}(I_1 - 3)^{\alpha_1} + K_2^{iso}(I_2 - 3)^{\alpha_2} + \varphi_1 \left[K_1^{ani1} (I_4 - 1)^{\beta_1} + K_2^{ani1} (I_5 - 1)^{\beta_2} \right]$$
(7)
+ $\varphi_2 \left[K_1^{ani2} (I_6 - 1)^{\gamma_1} + K_2^{ani2} (I_7 - 1)^{\gamma_2} \right] + K^{coup ani} (I_4 - 1)^{\xi} (I_6 - 1)^{\xi}$

Note that in [7] further coupling terms have been introduced, which have hardly influenced the results, and therefore are dropped here. The exponents α_i , β_i , γ_i , (i = 1, 2), and ξ are chosen to be integers larger than 2.

3 Delamination onset criterion

The onset of delamination can be determined on the basis of stress-strength relations. In particular, delamination occurs in pure interlaminar tension (mode I), pure interlaminar sliding shear (mode II), and pure interlaminar scissoring shear (mode III), if the corresponding interlaminar stress component exceeds the respective maximum interfacial strength. Here, the interlaminar stress components are denoted by σ_{33} , σ_{13} , and σ_{23} , respectively, where the 3-direction is normal to the considered interface. Then, the respective interfacial strengths are Z_{33} , Z_{13} , and Z_{23} .

To account for mixed-mode loading, the formulation of the onset criterion should incorporate the interaction of these modes. Due to the lack of available experimental data, failure criteria predicting the initiation of delamination have not been fully validated, and hence only few formulations exist. In this paper, the approach of Ye [9] is adopted, in which a quadratic interaction of modes is assumed:

if
$$\sigma_{33} > 0$$
: $\left(\frac{\sigma_{33}}{Z_{33}}\right)^2 + \left(\frac{\sigma_{31}}{Z_{31}}\right)^2 + \left(\frac{\sigma_{32}}{Z_{32}}\right)^2 \ge 1$ (8a)

if
$$\sigma_{33} \le 0$$
: $\left(\frac{\sigma_{31}}{Z_{31}}\right)^2 + \left(\frac{\sigma_{32}}{Z_{32}}\right)^2 \ge 1$ (8b)

As the formulation presented in this paper is capable of taking into account finite strains, it is important to accurately represent the according stress components. First of all, the stresses calculated by the present solid-shell formulation are expressed by the second Piola-Kirchhoff stress tensor **S**, which has to be pushed to the current configuration

$$\boldsymbol{\sigma} = \frac{1}{\det \mathbf{F}} \mathbf{F} \mathbf{S} \mathbf{F}^{\mathrm{T}}$$
(9)

where σ denotes the Cauchy stress tensor. From this, the interlaminar traction σ_n and the interlaminar resultant shear τ_n can be achieved by

$$\sigma_n = \boldsymbol{n}\,\boldsymbol{\sigma}\,\boldsymbol{n} \tag{10}$$

$$\tau_n = \sqrt{||\boldsymbol{n}\,\boldsymbol{\sigma}||^2 - \sigma_n^2} \tag{11}$$

denoting the normal vector of the considered interface by n. For consistency, the maximum interfacial strength in tension and resultant shear are referred to as Z_{σ} and Z_{τ} , respectively. Consequently, the condition for delamination onset reads

if
$$\sigma_n > 0$$
: $\left(\frac{\sigma_n}{Z_{\sigma}}\right)^2 + \left(\frac{\tau_n}{Z_{\tau}}\right)^2 \ge 1$ (12a)

if
$$\sigma_n \le 0$$
: $\left(\frac{\tau_n}{Z_\tau}\right)^2 \ge 1$ (12b)

This condition has to be checked in each loading step and in each interface of the laminated composite. Thus, the accurate prediction of the stress components in the interfaces is essential for a reliable prediction of the initiation of debonding. Since the layers are usually rather thin, solid elements are not suitable to achieve sufficient accuracy. To overcome this problem, spline approximations for the through-the-thickness stresses can be applied, as proposed in [11]. Even so, using solid elements in the thin shell-like applications should be avoided, and solid-shell elements are preferable.

Further, it should be noticed that this kind of criterion is suitable to predict the delamination onset, but delamination growth is not covered.

4 Solid-shell formulation

Using standard solid elements in thin structures would require a very high mesh density to predict the stress distribution with sufficient accuracy. Hence, the solid-shell element formulation is used alternatively to avoid inefficient computations. Furthermore, the different locking phenomena are cured by application of the EAS and ANS concepts. The following is based on the works of Schwarze and Reese [32–34].

4.1 Finite element framework and interpolation

The solid-shell concept is predicated on the two-field variational functional

$$g_1(\mathbf{u}, \mathbf{E}_e) = \int_{B_0} \mathbf{S}(\mathbf{E}) : \delta \mathbf{E}_c \, dV + g_{ext} = 0$$
 (13)

$$g_2(\mathbf{u}, \mathbf{E}_e) = \int_{B_0} \mathbf{S}(\mathbf{E}) : \delta \mathbf{E}_e \, d\mathbf{V} = 0$$
 (14)

where g_{ext} denotes the virtual work of the external loading. For this formulation, the total Green-Lagrange strain tensor E is split additively into the compatible part E_c and the enhanced part E_e coming from the EAS concept:

$$\mathbf{E} = \mathbf{E}_{\rm c} + \mathbf{E}_{\rm e} \tag{15}$$

The second Piola-Kirchhoff stress tensor S(E) is a function of the total Green-Lagrange strain tensor E. Note that S depends additionally on a set of internal variables in the elastoplastic case.

In this work, isoparametric eight-node hexahedral finite elements are considered, such that both the position vector of the reference configuration $\mathbf{X}(\boldsymbol{\xi}) = [X_1, X_2, X_3]^T$ and the displacement vector $\mathbf{U}(\boldsymbol{\xi}) = [U_1, U_2, U_3]^T$ are approximated within the element by

$$X_{i} = \sum_{I=1}^{8} N_{I} X_{iI}$$
 and $U_{i} = \sum_{I=1}^{8} N_{I} U_{iI}$ (i = 1, 2, 3) (16)

using tri-linear shape functions

$$N_I = 1/8(1 + \xi_I \xi)(1 + \eta_I \eta)(1 + \zeta_I \zeta) \quad (I = 1, ..., 8)$$
(17)

The position vector of the current (deformed) configuration reads

$$\mathbf{x}(\boldsymbol{\xi}) = \mathbf{X}(\boldsymbol{\xi}) + \mathbf{U}(\boldsymbol{\xi}) \tag{18}$$

Then, introducing $\mathbf{D} = \partial \mathbf{U} / \partial \boldsymbol{\xi}$, the Jacobian matrices J and $\tilde{\mathbf{J}}$ of the reference and the current configuration, respectively, can be written as follows:

$$\mathbf{J} = \frac{\partial \mathbf{X}}{\partial \boldsymbol{\xi}} = [\mathbf{J}_1, \mathbf{J}_2, \mathbf{J}_3] \quad \text{and} \quad \tilde{\mathbf{J}} = \frac{\partial \mathbf{x}}{\partial \boldsymbol{\xi}} = \mathbf{J} + \mathbf{D} = \begin{bmatrix} \tilde{\mathbf{J}}_1, \tilde{\mathbf{J}}_2, \tilde{\mathbf{J}}_3 \end{bmatrix}$$
(19)

The columns of J and J represent the covariant base vectors with respect to the reference and current configuration, respectively. The polynomial form of the Jacobian matrices defined in (19) is obtained by means of the polynomials

$$\mathbf{J} = \mathbf{J}^0 + \xi \mathbf{J}^{\xi} + \eta \mathbf{J}^{\eta} + \zeta \mathbf{J}^{\zeta} + \xi \eta \mathbf{J}^{\xi\eta} + \eta \zeta \mathbf{J}^{\eta\zeta} + \xi \zeta \mathbf{J}^{\xi\zeta}$$
(20)

$$\mathbf{D} = \mathbf{D}^{0} + \xi \mathbf{D}^{\xi} + \eta \mathbf{D}^{\eta} + \zeta \mathbf{D}^{\zeta} + \xi \eta \mathbf{D}^{\xi \eta} + \eta \zeta \mathbf{D}^{\eta \zeta} + \xi \zeta \mathbf{D}^{\xi \zeta}$$
(21)

The contravariant base vectors with respect to the initial configuration and the current configuration are denoted by

$$\mathbf{H}_{i} = \frac{\partial \xi_{i}}{\partial X_{j}} \mathbf{e}_{j} = j_{ij} \mathbf{e}_{j} \quad \text{and} \quad \tilde{\mathbf{H}}_{i} = \frac{\partial \xi_{i}}{\partial x_{j}} \mathbf{e}_{j} = \tilde{j}_{ij} \mathbf{e}_{j}$$
(22)

These represent the rows of the inverse Jacobian matrices \mathbf{J}^{-1} and $\tilde{\mathbf{J}}^{-1}$, respectively, the coefficients of which are denoted by $j_{ij} = (\mathbf{J}^{-1})_{ij}$ and $\tilde{j}_{ij} = (\tilde{\mathbf{J}}^{-1})_{ij}$. With this definition, the Green-Lagrange strain tensor can be written in terms of its Cartesian and covariant components E_{ij} and $\bar{E}_{ij} = E_{\xi_i\xi_j}$, respectively,

$$\mathbf{E} = \mathbf{E}_{ij} \, \mathbf{e}_i \otimes \mathbf{e}_j = \bar{\mathbf{E}}_{ij} \, \mathbf{H}_i \otimes \mathbf{H}_j \tag{23}$$

Denoting the Voigt notation by $(\hat{\bullet})$ and exploiting symmetry as well as $\Gamma_{ij} = 2 E_{ij}$, the latter can be stored into the 6×1 vectors

$$\hat{\mathbf{E}} = \{ E_{11}, \, E_{22}, \, E_{33}, \, \Gamma_{12}, \, \Gamma_{23}, \, \Gamma_{13} \}^T \tag{24}$$

$$\hat{\bar{\mathbf{E}}} = \{ E_{\xi\xi}, E_{\eta\eta}, E_{\zeta\zeta}, \Gamma_{\xi\eta}, \Gamma_{\eta\zeta}, \Gamma_{\xi\zeta} \}^T$$
(25)

These can be transformed one to the other with the relation $\hat{\mathbf{E}} = \mathbf{T} \, \hat{\bar{\mathbf{E}}}$, where

	j_{11}^2	j_{21}^2	j_{31}^2	j11j21	j21j31	j11j31	
$\mathbf{T} =$	j_{12}^2	j_{22}^2	j_{32}^2	j12j22	j22j32	j12j32	(26)
	j_{13}^2	j_{23}^2	j_{33}^2	j13j23	j23j33	j13j33	
	$2 j_{11} j_{12}$	$2j_{21}j_{22}$	$2 j_{31} j_{32}$	$j_{12}j_{21}+j_{11}j_{22}$	$j_{22}j_{31}+j_{21}j_{32}$	$j_{12}j_{31}+j_{11}j_{32}$	
	2 j ₁₂ j ₁₃	$2j_{22}j_{23}$	2 j ₃₂ j ₃₃	$j_{13}j_{22}+j_{12}j_{23}$	j ₂₃ j ₃₂ +j ₂₂ j ₃₃	j13j32+j12j33	
	2 j ₁₁ j ₁₃	$2j_{21}j_{23}$	$2 j_{31} j_{33}$	$j_{13}j_{21} {+} j_{11}j_{23}$	j ₂₃ j ₃₁ +j ₂₁ j ₃₃	j ₁₃ j ₃₁ +j ₁₁ j ₃₃	

4.2 Green-Lagrange strain field

Consequently, the compatible Green-Lagrange strain is written in the form $\hat{\mathbf{E}}_{c} = \mathbf{T} \hat{\mathbf{E}}_{c}$. To get the components of the compatible Green-Lagrange strain tensor $\hat{\mathbf{E}}_{c}$ in polynomial form, both the Jacobian matrix J and the displacement gradient D are split column-wise:

$$\mathbf{J}_{1} = \mathbf{J}_{1}^{0} + \eta \, \mathbf{J}_{1}^{\eta} + \zeta \, \mathbf{J}_{1}^{\zeta} + \eta \zeta \, \mathbf{J}_{1}^{\eta \zeta} \qquad \mathbf{D}_{1} = \mathbf{D}_{1}^{0} + \eta \, \mathbf{D}_{1}^{\eta} + \zeta \, \mathbf{D}_{1}^{\zeta} + \eta \zeta \, \mathbf{D}_{1}^{\eta \zeta}$$
(27a)

$$\mathbf{J}_{2} = \mathbf{J}_{2}^{0} + \xi \, \mathbf{J}_{2}^{\xi} + \zeta \, \mathbf{J}_{2}^{\zeta} + \xi \zeta \, \mathbf{J}_{2}^{\xi \zeta} \qquad \mathbf{D}_{2} = \mathbf{D}_{2}^{0} + \xi \, \mathbf{D}_{2}^{\xi} + \zeta \, \mathbf{D}_{2}^{\zeta} + \xi \zeta \, \mathbf{D}_{2}^{\xi \zeta}$$
(27b)

$$\mathbf{J}_{3} = \mathbf{J}_{3}^{0} + \xi \, \mathbf{J}_{3}^{\xi} + \eta \, \mathbf{J}_{3}^{\eta} + \xi \eta \, \mathbf{J}_{3}^{\xi \eta} \qquad \mathbf{D}_{3} = \mathbf{D}_{3}^{0} + \xi \, \mathbf{D}_{3}^{\xi} + \eta \, \mathbf{D}_{3}^{\eta} + \xi \eta \, \mathbf{D}_{3}^{\xi \eta} \qquad (27c)$$

Hence, the covariant compatible Green-Lagrange strain components are given by

$$E_{c\xi\xi} = \mathbf{J}_1^{\mathrm{T}} \mathbf{D}_1 + 1/2 \mathbf{D}_1^{\mathrm{T}} \mathbf{D}_1 \qquad \Gamma_{c\xi\eta} = \mathbf{J}_1^{\mathrm{T}} \mathbf{D}_2 + \mathbf{J}_2^{\mathrm{T}} \mathbf{D}_1 + \mathbf{D}_1^{\mathrm{T}} \mathbf{D}_2 \qquad (28a)$$

$$\mathbf{E}_{\mathrm{c}\,\eta\eta} = \mathbf{J}_{2}^{\mathrm{T}}\mathbf{D}_{2} + 1/2\,\mathbf{D}_{2}^{\mathrm{T}}\mathbf{D}_{2} \qquad \Gamma_{\mathrm{c}\,\eta\zeta} = \mathbf{J}_{2}^{\mathrm{T}}\mathbf{D}_{3} + \mathbf{J}_{3}^{\mathrm{T}}\mathbf{D}_{2} + \mathbf{D}_{2}^{\mathrm{T}}\mathbf{D}_{3} \qquad (28b)$$

$$E_{c\zeta\zeta} = \mathbf{J}_3^{\mathrm{T}} \mathbf{D}_3 + 1/2 \, \mathbf{D}_3^{\mathrm{T}} \mathbf{D}_3 \qquad \Gamma_{c\xi\zeta} = \mathbf{J}_1^{\mathrm{T}} \mathbf{D}_3 + \mathbf{J}_3^{\mathrm{T}} \mathbf{D}_1 + \mathbf{D}_1^{\mathrm{T}} \mathbf{D}_3 \qquad (28c)$$

To cure curvature thickness locking, the ANS concept is implemented. For this, the covariant compatible strain terms $E_{c\zeta\zeta}|_{\boldsymbol{\xi}_K} := E_{c\zeta\zeta}^K$ are evaluated at the sampling points K = A, ..., D, see Fig. 1, as proposed in [42].



$$\begin{aligned} \boldsymbol{\xi}_{A} &= (-1, -1, 0)^{T} \quad \boldsymbol{\xi}_{E} = (-1, 0, -1)^{T} \quad \boldsymbol{\xi}_{J} = (0, -1, -1)^{T} \\ \boldsymbol{\xi}_{B} &= (1, -1, 0)^{T} \quad \boldsymbol{\xi}_{F} = (1, 0, -1)^{T} \quad \boldsymbol{\xi}_{K} = (0, 1, -1)^{T} \\ \boldsymbol{\xi}_{C} &= (1, 1, 0)^{T} \quad \boldsymbol{\xi}_{G} = (1, 0, 1)^{T} \quad \boldsymbol{\xi}_{L} = (0, 1, 1)^{T} \\ \boldsymbol{\xi}_{D} &= (-1, 1, 0)^{T} \quad \boldsymbol{\xi}_{H} = (-1, 0, 1)^{T} \quad \boldsymbol{\xi}_{M} = (0, -1, 1)^{T} \end{aligned}$$

Figure 1: Sampling points of the ANS concept at reference element

Thereby, the covariant compatible strains can be interpolated within the shell mid plane of the reference element by means of bilinear ansatz functions

$$\bar{N}_{K} = 1/4(1 + \xi_{K}\xi)(1 + \eta_{K}\eta)$$
(29)

to be evaluated in the points K = A, ..., D. In consequence, the assumed transverse normal strain distribution reads

$$E_{c\zeta\zeta}^{ANS} = \bar{N}_{A}E_{c\zeta\zeta}^{A} + \bar{N}_{B}E_{c\zeta\zeta}^{B} + \bar{N}_{C}E_{c\zeta\zeta}^{C} + \bar{N}_{D}E_{c\zeta\zeta}^{D} = \sum_{K=A}^{D} \bar{N}_{K}E_{c\zeta\zeta}^{K}$$
(30)

In order to overcome the transverse shear locking, following [31], four sampling points K = E, ..., H are used for the transverse shear term $\Gamma_{c \eta \zeta}|_{\boldsymbol{\xi}_{K}} := \Gamma_{c \eta \zeta}^{K}$ and K = J, ..., M for $\Gamma_{c \xi \zeta}|_{\boldsymbol{\xi}_{K}} := \Gamma_{c \xi \zeta}^{K}$, see again Fig. 1. Using the ansatz functions (29) for the respective points, the assumed transverse shear terms read

$$\Gamma_{c\,\eta\zeta}^{ANS} = \sum_{K=E}^{H} \bar{N}_{K} \Gamma_{c\,\eta\zeta}^{K} \quad \text{and} \quad \Gamma_{c\,\xi\zeta}^{ANS} = \sum_{K=J}^{M} \bar{N}_{K} \Gamma_{c\,\xi\zeta}^{K}$$
(31)

The present solid-shell formulation utilizes a reduced integration scheme within the shell plane (using one integration point), whereas a full integration is used in thickness direction, which allows for choosing arbitrary numbers of integration points (at least two), see Fig. 2. Thus, all integration points are located on the normal through the center of the element defined by $\boldsymbol{\xi}^* := (0, 0, \zeta)^T$.



Figure 2: Solid-shell element with integration points at $\boldsymbol{\xi} = \boldsymbol{\xi}^{\star} := (0, 0, \zeta)^{\mathrm{T}}$

To cure volumetric locking as well as Poisson thickness locking, the EAS concept is adopted. These locking effects are treated on the level of the integration points, which can be expressed by $\hat{\mathbf{E}}_e = \hat{\mathbf{E}}_e^*$, indicating values to be evaluated in the integration points by *. Since in (30) the assumed transverse normal strain $\mathbf{E}_{e\zeta\zeta}^{ANS}$ has been defined independently of ζ , the according value $\mathbf{E}_{e\zeta\zeta}$ is constructed as being linear in ζ in order to overcome the locking effects, which reads

$$\hat{\mathbf{E}}_{\mathrm{e}} = \hat{\mathbf{E}}_{\mathrm{e}}^{\star} = \mathbf{T}^0 \, \bar{\mathbf{B}}_{\mathrm{e}}^{\star} \, \mathrm{W}_{\mathrm{e}} \tag{32}$$

in which the interpolation matrix $\bar{\mathbf{B}}_{e}^{\star} = [0, 0, \zeta, 0, 0, 0]^{\mathrm{T}}$ requires only one EAS degreeof-freedom W_{e} . Here, \mathbf{T}^{0} is the transformation matrix (26) evaluated in the center of the element.

In order to achieve a polynomial decoupling of the compatible Green-Lagrange strain tensor, $\hat{\mathbf{E}}_c = \mathbf{T} \, \hat{\bar{\mathbf{E}}}_c$, a Taylor expansion of the inverse Jacobian matrix is carried out with respect to the center of the element

$$\mathbf{J}^{-1} \approx \mathbf{J}^{-1} \Big|_{\boldsymbol{\xi}=0} + \sum_{i=1}^{3} \left| \mathbf{J}_{,\xi_{i}}^{-1} \right|_{\boldsymbol{\xi}=0} \xi_{i} = \mathbf{J}^{-1} \Big|_{\boldsymbol{\xi}=0} + \sum_{i=1}^{3} \left(\mathbf{J}^{0} \right)^{-1} \mathbf{J}^{\xi_{i}} (\mathbf{J}^{0})^{-1} \xi_{i}$$
(33)

up to the linear terms. The goal is reached by exploiting the Taylor expansion of

$$\mathbf{J}\mathbf{J}^{-1} \approx (\mathbf{J}\mathbf{J}^{-1})\big|_{\boldsymbol{\xi}=0} + \sum_{i=1}^{3} (\mathbf{J}\mathbf{J}^{-1})_{,\xi_{i}}\big|_{\boldsymbol{\xi}=0} \xi_{i}$$
(34)

as well as $JJ^{-1} = I$, which must hold for arbitrary $\boldsymbol{\xi} = (\xi, \eta, \zeta)^{T} = (\xi_1, \xi_2, \xi_3)^{T}$. Introducing the coefficients of (33) into (26), the transformation matrix is given by

$$\mathbf{T} \approx \mathbf{T}^0 + \xi \, \mathbf{T}^{\xi} + \eta \, \mathbf{T}^{\eta} + \zeta \, \mathbf{T}^{\zeta} \tag{35}$$

in polynomial form, where terms of higher order have been dropped, as has been shown to be sufficient in [32]. Nevertheless, using the approximation (26), the Cartesian compatible strain still represents a polynomial of high order. For this reason, a Taylor expansion of the Cartesian compatible Green-Lagrange strain

$$\hat{\mathbf{E}}_{c} = \mathbf{T} \, \hat{\mathbf{E}}_{c} \approx \hat{\mathbf{E}}_{c} \Big|_{\boldsymbol{\xi}=0} + \sum_{i=1}^{3} \hat{\mathbf{E}}_{c,\xi_{i}} \Big|_{\boldsymbol{\xi}=0} \xi_{i} + \frac{1}{2} \sum_{i=1}^{3} \sum_{j\neq i=1}^{3} \hat{\mathbf{E}}_{c,\xi_{i}\xi_{j}} \Big|_{\boldsymbol{\xi}=0} \xi_{i}\xi_{j} (36)$$

$$:= \underbrace{\hat{\mathbf{E}}_{c}^{0} + \zeta \hat{\mathbf{E}}_{c}^{\zeta}}_{\hat{\mathbf{E}}_{c}^{\star}} + \underbrace{\xi \hat{\mathbf{E}}_{c}^{\xi} + \eta \hat{\mathbf{E}}_{c}^{\eta} + \xi \eta \hat{\mathbf{E}}_{c}^{\xi\eta} + \eta \zeta \hat{\mathbf{E}}_{c}^{\eta\zeta} + \xi \zeta \hat{\mathbf{E}}_{c}^{\xi\zeta}}_{\hat{\mathbf{E}}_{c}^{\star}} \tag{37}$$

is also carried out with respect to the center of the element. The hourglass strain term $\hat{\mathbf{E}}_{c}^{hg}$ represents an excellent basis for the construction of the hourglass stabilization. However, $\hat{\mathbf{E}}_{c}^{\star}$ is no longer quadratic in ζ . Thus, the according quadratic term is added:

$$\hat{\mathbf{E}}_{c}^{\star} := \hat{\mathbf{E}}_{c}^{0} + \zeta \hat{\mathbf{E}}_{c}^{\zeta} + \zeta^{2} \hat{\mathbf{E}}_{c}^{\zeta\zeta}$$
(38)

4.3 2nd Piola-Kirchhoff stress tensor

In this section, an efficient stress state $\hat{\mathbf{S}} := \hat{\mathbf{S}}^* + \hat{\mathbf{S}}^{hg}$ is derived for the reduced integration, which is represented by the second Piola-Kirchhoff stress tensor. Here, $\hat{\mathbf{S}}^*$ is computed at the integration points placed at $\boldsymbol{\xi} = \boldsymbol{\xi}^*$ and must be able to take into account the highly nonlinear stress distributions in thickness direction. The hourglass stress part $\hat{\mathbf{S}}^{hg}$ has to guarantee that the element is free of hourglass instabilities. Following [27], a Taylor expansion of the stress field is carried out with respect to $\boldsymbol{\xi} = \boldsymbol{\xi}^*$.

$$\hat{\mathbf{S}} \approx \hat{\mathbf{S}} \bigg|_{\boldsymbol{\xi} = \boldsymbol{\xi}^{\star}} + \frac{\partial \hat{\mathbf{S}}}{\partial \boldsymbol{\xi}} \bigg|_{\boldsymbol{\xi} = \boldsymbol{\xi}^{\star}} (\boldsymbol{\xi} - 0) + \frac{\partial \hat{\mathbf{S}}}{\partial \eta} \bigg|_{\boldsymbol{\xi} = \boldsymbol{\xi}^{\star}} (\eta - 0)$$
(39)

$$= \hat{\mathbf{S}}(\hat{\mathbf{E}}^{\star}) + \underbrace{\frac{\partial \hat{\mathbf{S}}(\hat{\mathbf{E}})}{\partial \hat{\mathbf{E}}}}_{\hat{\mathbf{C}}^{\star}} \left(\frac{\partial \hat{\mathbf{E}}}{\partial \xi} \bigg|_{\boldsymbol{\xi} = \boldsymbol{\xi}^{\star}} \xi + \frac{\partial \hat{\mathbf{E}}}{\partial \eta} \bigg|_{\boldsymbol{\xi} = \boldsymbol{\xi}^{\star}} \eta \right)$$
(40)

$$= \hat{\mathbf{S}}^{\star} + \underbrace{\hat{\mathbf{C}}^{\star}(\xi \hat{\mathbf{E}}_{c}^{\xi} + \eta \hat{\mathbf{E}}_{c}^{\eta} + \eta \zeta \hat{\mathbf{E}}_{c}^{\eta \zeta} + \xi \zeta \hat{\mathbf{E}}_{c}^{\xi \zeta})}_{:= \hat{\mathbf{S}}^{\text{hg}}}$$
(41)

The tangent $\hat{\mathbf{C}}^*$ is nonlinear in the thickness direction ζ but independent of ξ and η . In order to enable an analytical integration of the hourglass stabilization terms, $\hat{\mathbf{C}}^*$ is replaced by the deviatoric part of the linear-elastic material tangent $\hat{\mathbf{C}}^{hg}$, which in Voigt notation reads

$$\hat{\mathbf{C}}^{\rm hg} = \mu^{\rm hg} \begin{bmatrix} 4/3 & -2/3 & -2/3 & 0 & 0 & 0 \\ -2/3 & 4/3 & -2/3 & 0 & 0 & 0 \\ -2/3 & -2/3 & 4/3 & 0 & 0 & 0 \\ 0 & 0 & 0 & 1 & 0 & 0 \\ 0 & 0 & 0 & 0 & 1 & 0 \\ 0 & 0 & 0 & 0 & 0 & 1 \end{bmatrix}$$
(42)

and which only depends on the artificial hourglass shear modulus μ^{hg} . In elastic problems μ^{hg} is equal to the elastic shear modulus $\mu = E/(2(1 + \nu))$, whereas in elastoplasticity it reads as follows:

$$\mu^{\rm hg} = \frac{1}{2} \sqrt{\frac{\mathbf{S}^{\star \, \rm dev} : \mathbf{S}^{\star \, \rm dev}}{\mathbf{E}^{\star \, \rm dev} : \mathbf{E}^{\star \, \rm dev}}} \tag{43}$$

Here, the superscript "dev" indicates the deviatoric part of the considered term. Summing up over the number of integration points $(i = 1, ..., n_{ip})$ leads to the following effective hourglass shear modulus

$$\mu_{\text{eff}}^{\text{hg}} = \sum_{i=1}^{n_{\text{ip}}} \mu_{i}^{\text{hg}} \,\omega_{i} = \frac{1}{2} \sum_{i=1}^{n_{\text{ip}}} \left(\sqrt{\frac{\mathbf{S}^{\star \,\text{dev}} : \mathbf{S}^{\star \,\text{dev}}}{\mathbf{E}^{\star \,\text{dev}} : \mathbf{E}^{\star \,\text{dev}}}} \right) \bigg|_{i} \omega_{i} \tag{44}$$

where the weighting factors ω_i are scaled, such that $\sum_{i=1}^{n_{ip}} \omega_i = 1$ holds.

4.4 Discretized weak form

Introducing the virtual form of the Cartesian enhanced Green-Lagrange strain $\delta \dot{\mathbf{E}}_e$ together with (41), Eq. (14) reads

$$g_{2}^{e} \approx \int_{\Omega^{e}} \delta \hat{\mathbf{E}}_{e}^{T} \, \hat{\mathbf{S}} \, J^{0} \, d\Omega^{e} = \int_{\Omega^{e}} \delta \hat{\mathbf{E}}_{e}^{\star T} \, \hat{\mathbf{S}}^{\star} \, J^{0} \, d\Omega^{e} = \delta W_{e} \, R_{w}^{\star} = 0$$
(45)

Note that the infinitesimal volume element $dV^e = J d\Omega^e$ has been approximated by means of $dV^e \approx J^0 d\Omega^e$. Thereby, the integral $\int_{\Omega^e} \delta \hat{\mathbf{E}}_e^{\star T} \hat{\mathbf{S}}^{\star} J^0 d\Omega^e$ vanishes, because (32) is only linear in ζ . Further, the virtual forms of (37) and (38) together with (41) are incorporated into (13), which –on the element level– can be written as

$$g_1^e - g_{ext}^e \approx \int_{\Omega^e} \delta \mathbf{E}_c^T \, \hat{\mathbf{S}} \, J^0 \, d\Omega^e$$
(46)

$$= \int_{\Omega^{e}} \delta \mathbf{E}_{c}^{\star T} \, \hat{\mathbf{S}}^{\star} \, \mathbf{J}^{0} \, \mathrm{d}\Omega^{e} + \int_{\Omega^{e}} \delta \mathbf{E}_{c}^{\mathrm{hg } T} \, \hat{\mathbf{S}}^{\mathrm{hg }} \, \mathbf{J}^{0} \, \mathrm{d}\Omega^{e}$$
(47)

$$= \delta \mathbf{U}_{\mathrm{e}}^{\mathrm{T}} \mathbf{R}_{\mathrm{u}}^{\star} + \delta \mathbf{U}_{\mathrm{e}}^{\mathrm{T}} \mathbf{R}_{\mathrm{u}}^{\mathrm{hg}}$$
(48)

Again, all terms being linear in the natural coordinates drop out. This leads to the desired decoupling of the parts corresponding to the integration point and the hourglass stabilization. Since the hourglass stress has deviatoric character (see Eqs. (41) and (42)), the hourglass residual vector \mathbf{R}_{u}^{hg} simplifies to

$$\mathbf{R}_{u}^{hg} = \int_{-1}^{1} \int_{-1}^{1} \int_{-1}^{1} \mathbf{B}_{c}^{hg \, dev \, T} \, \hat{\mathbf{S}}^{hg} \, \mathbf{J}^{0} \, d\xi \, d\eta \, d\zeta$$

$$= \underbrace{\frac{8}{3} \mathbf{J}^{0} \mathbf{B}_{c}^{\xi \, dev \, T} \, \hat{\mathbf{C}}^{hg} \, \hat{\mathbf{E}}_{c}^{\xi \, dev}}_{:= \mathbf{R}_{u}^{\xi \, hg}} + \underbrace{\frac{8}{3} \mathbf{J}^{0} \mathbf{B}_{c}^{\eta \, dev \, T} \, \hat{\mathbf{C}}^{hg} \, \hat{\mathbf{E}}_{c}^{\eta \, dev}}_{:= \mathbf{R}_{u}^{\eta \, hg}}$$

$$+ \underbrace{\frac{8}{9} \mathbf{J}^{0} \mathbf{B}_{c}^{\eta \zeta \, dev \, T} \, \hat{\mathbf{C}}^{hg} \, \hat{\mathbf{E}}_{c}^{\eta \zeta \, dev}}_{:= \mathbf{R}_{u}^{\eta \zeta \, hg}} + \underbrace{\frac{8}{9} \mathbf{J}^{0} \mathbf{B}_{c}^{\xi \zeta \, dev \, T} \, \hat{\mathbf{C}}^{hg} \, \hat{\mathbf{E}}_{c}^{\xi \zeta \, dev}}_{:= \mathbf{R}_{u}^{\xi \zeta \, hg}} \tag{49}$$

in which the integration over the element domain is performed analytically. Further, terms being bilinear in $\xi\eta$ drop out, because \hat{S}^{hg} does not include any summand depending on that.

5 Numerical Example

The proposed method was applied to a mechanically fastened joint in a composite sheet consisting of 8 layers in a symmetric assembly $(0^{\circ}, 90^{\circ}, +45^{\circ}, -45^{\circ})_s$, each of which was made of unidirectional CFRP (*Hexel T300/914*). The sheet's dimensions were: length 200 mm, height 2 mm, and width 36 mm. It contained two circular wholes of diameter 6 mm, which were located at a distance of 36 mm from the end of the sheet, measured from the whole's center. In each of the wholes, a very stiff bolt was placed tight-fitting and then moved displacement-driven in longitudinal outward direction of the sheet, applying 0.01 mm per time step.

Due to symmetry of the system, only one eighth of the sheet was considered in the computation (see Fig. 3), applying symmetric boundary conditions. In addition, the elements at the upper surface surrounding the whole were fixed in thickness direction to simulate a finger-tight washer. In order to incorporate delamination, interface elements were located between all layers, which were furnished with material properties of the matrix alone. The latter were assumed to be ten times thinner than the layers. Whereas the described solid-shell element was used for both layers and interfaces – leading to a total number of 5800 solid-shell elements with 7164 nodes– the bolt was discretized by 375 hexahedral solids with 624 (see Fig. 4).

The according material parameters for the carbon fibres –taken from the Torayca T300 data sheet– and the epoxy matrix –taken from the HexPly 914 product data– are given in Table 1. From these, the non-zero parameters for the described model can be calculated, taking into account the fibre volume fraction $\varphi_1 = 60^\circ$.

$$\Lambda = 6300 \text{ MPa} \qquad \mu = 1383 \text{ MPa} \qquad K_1^{anv1} = 1.15 \times 10^5 \text{ MPa} \qquad \beta_1 = 2 \qquad (50)$$



Figure 3: Geometry and mesh

230
3.9
1.4
0.41

Table 1: Material properties

For the interfacial strengths, the values reported in [11] are adopted

$$Z_{33} = 76 \text{ MPa}$$
 $Z_{13} = 79 \text{ MPa}$ $Z_{23} = 79 \text{ MPa}$ (51)

giving the following parameters for the delamination onset criterion (12):

$$Z_{\sigma} = 76 \text{ MPa} \qquad \qquad Z_{\tau} = 79 \sqrt{2} \text{ MPa} \qquad (52)$$

In fact, to enforce the delamination at an earlier stage of the computation, both the stresses and the interfacial strengths were divided by 10.

The location of delamination initiation is shown in Fig. 5, which corresponds to the time step, in which the delamination onset condition is met first. As one can see, delamination occurs at first close to the boundary of the whole in the lower surface of the model, which is the middle surface of the sheet. The location of delamination is reasonable in agreement with the results presented in [11]. Furthermore, experimental



Figure 4: Detailed view on bolt and whole

data for this problem can be found in [43]. Therein, the cross head displacement corresponding to delamination onset is approximately given by 1.15 mm, whereas in the current calculation, the delamination initiates between 1.2 mm and 1.3 mm.

6 Conclusion

For many technical applications of fibre-reinforced composites, predicting the onset of delamination is essential for appropriately designing the considered structure. For this, a delamination onset criterion based on stress-strength relations has been suggested in this paper, which requires an accurate representation of the through-the-thickness stress distribution. The proposed solid-shell element is particularly suitable to achieve the required accuracy especially in the thin shell-like applications considered here. The formulation allows for including woven fabrics with two different families of fibres, incorporating a fully three-dimensional, anisotropic, micro-mechanically motivated material model. Concluding, the proposed method is capable of predicting the initiation of delamination of fibre-reinforced composites in shell-like structures accounting for the anisotropic material behaviour.



Figure 5: Resulting zone of delamination onset

References

- G. Holzapfel, R. Eberlein, P. Wriggers, H. Weizsäcker, "A new axisymmetrical membrane element for anisotropic, finite strain analysis of arteries", Commun Numer Methods Engng, 12, 507–517, 1996.
- [2] J. Weiss, B. Maker, S. Govindjee, "Finite element implementation of incompressible, transversely isotropic hyperelasticity", Comput Methods Appl Mech Engrg, 135, 107–128, 1996.
- [3] M.Rüter, E. Stein, "Analysis, finite element computation and error estimation in transversal isotropic nearly incompressible finite elasticity", Comput Methods Appl Mech Engrg, 190, 519–541, 2000.
- [4] J. Bonet, A. Burton, "A simple, orthotropic transversely isotropic hyperelastic constitutive equation for large strain computations", Comput Methods Appl Mech Engrg, 162, 151–164, 1998.
- [5] L. Mishnaevsky Jr., H. Qing, "Micromechanical modelling of mechanical behavior and strength of wood: State-of-the-art review", Comp Mater Sci, 44, 363–370, 2008.
- [6] E. Marklund, J. Varna, "Micromechanical modelling of wood fibre composites", Plast Rubber Compos, 38(2–4), 118–123, 2009.
- [7] S. Reese, "Meso-macro modelling of fibre-reinforced rubber-like composites exhibiting large elastoplastic deformation", Int J Solids & Struct, 40, 951–980,

2003.

- [8] Z. Hashin, A. Rotem, "A fatigue failure criterion for fibre reinforced materials", J Compos Mater, 7, 448–464, 1973.
- [9] L. Ye, "Role of matrix resin in delamination onset and growth in composite laminates", Compos Sci Technol, 33 (4), 257–277, 1988.
- [10] C.G. Davila, E.R. Johnson, "Analysis of delamination initiation in postbuckled dropped-ply laminates", AIAA J, 31, 721–727, 1993.
- [11] P.P. Camanho, F.L. Matthews, "Delamination onset prediction in mechanically fastened joints", J Compos Mater, 33, 906–927, 1999.
- [12] A. Turon, P.P. Camanho, J. Costa, C.G. Davila, "A damage model for the simulation of delamination in advanced composites under variable-mode loading", Mech Mater, 38, 1072–1089, 2006.
- [13] T.K. O'Brien, "Interlaminar fracture toughness: The long and winding road to standardization", Composites Part B, 29 (1), 57–62, 1998.
- [14] S. Liu, "Quasi-impact damage initiation and growth of thick-section and toughened composite materials", Int J Solids & Struct, 31, 3079–3098, 1999.
- [15] Z. Zou, S.R. Reid, S. Li, P.D. Soden, "Modelling interlaminar and intralaminar damage in filament wound pipes under quasi-static indentation", J Compos Mater, 36, 477–499, 2002.
- [16] Te Tay, "Characterization and analysis of delamination fracture in composites: An overview of developments rom 1990 to 2001", Appl Mech Rev, 56 (1), 1–32, 2003.
- [17] R. Krueger, "Virtual crack closure technique: History, approach, and applications", Appl Mech Rev, 57 (2), 109–143, 2004.
- [18] R. de Borst, J.J.C. Remmers, "Computational modelling of delamination", Compos Sci Technol, 66, 713–722, 2006.
- [19] C. Balzani, W. Wagner, "An interface element for the simulatino of delamination in unidirectional fibre-reinforced composite laminates", Eng Fract Mech, 75, 2597–2615, 2008.
- [20] M.V. Cid Alfaro, A.S.J. Suiker, R. de Borst, J.J.C. Remmers, "Analysis of fracture and delamination in laminates using 3D numerical modelling", Eng Fract Mech, 76, 761–780, 2009.
- [21] C. Whang, H. Zhang, G. Shi, "3D Finite element simulatin of impact damage of laminated plates using solid-shell interface elements", Appl Mech Mater, 130-134, 766–770, 2012.
- [22] R. Cardoso, J. Yoon, "One point quadrature shell elements with through-thickness stretch", Comput Methods Appl Mech Engrg, 194, 1161–1199, 2005.
- [23] S. Klinkel, F. Gruttmann, W. Wagner, "A mixed shell formulation accounting for thickness strains and finite strain 3D material models", Int J Numer Methods Engng, 74, 945–970, 2008.
- [24] D. Kim, K. Bathe, "A 4-node 3D-shell element to model shell surface tractions and incompressible behavior", Comp & Struct, 86, 2027–2041, 2008.
- [25] R. Valente, R. Alves de Sousa, R. Natal Jorge, "An enhanced strain 3D element for large deformation elastoplastic thin shell applications", Comput Mech, 34,

38–52, 2004.

- [26] R. Alves de Sousa, R. Cardoso, R. Valente, J. Yoon, J. Gracio, R. Natal Jorge, "A new one-point quadrature enhanced assumed strain (EAS) solid shell element with multiple integration points along thickness–Part II: Nonlinear applications", Int J Numer Methods Engng, 67, 160–188, 2006.
- [27] S. Reese, "A large deformation solid-shell concept based on reduced integration with hourglass stabilization", Int J Numer Methods Engng, 69, 1671–1716, 2007.
- [28] X. Tan, L. Vu-Quoc, "Efficient and accurate multilayer solid-shell element: Nonlinear materials at finite strain", Int J Numer Methods Engng, 63, 2124–2170, 2005.
- [29] K. Kim, G. Liu, S. Han, "A resultant 8-node solid-shell element for geometrically nonlinear analysis", Comput Mech, 35, 315–331, 2005.
- [30] S. Klinkel, F. Gruttmann, W. Wagner, "A robust nonlinear solid-shell element based on a mixed variational formulation", Comput Methods Appl Mech Engrg, 195, 179–201, 2006.
- [31] R. Cardoso, J. Yoon, M. Mahardika, S. Choudhry, R. Alves de Sousa, R. Valente, "Enhanced assumed strain (EAS) and assumed natural strain (ANS) methods for one-point quadrature solid-shell elements", Int J Numer Methods Engng, 75, 156–187, 2008.
- [32] M. Schwarze, S. Reese, "A reduced integration solid-shell element based on the EAS and the ANS concept–geometrically linear problems", Int J Numer Methods Engng, 80, 1322–1355, 2009.
- [33] M. Schwarze, I. Vladimirov, S. Reese, "Sheet metal forming and springback simulation by means of a new reduced integration solid-shell finite element technology", Comput Methods Appl Mech Engrg, 200, 454–476, 2011.
- [34] M. Schwarze, S. Reese, "A reduced integration solid-shell finite element based on the EAS and the ANS concept - large deformation problems", Int J Numer Methods Engng, 85, 289–329, 2011.
- [35] T. Roy, P. Manikandan, D. Chakraborty, "Improved shell finite element for piezothermoelastic analysis of smart fiber reinforced composite structures", Finite Elem Anal Des, 46(9), 710–720, 2010.
- [36] L.-Q. Yao, L. Lu, "An Electric Node Concept for Solid-Shell Elements for Laminate Composite Piezoelectric Structures", ASME J Appl Mech, 72, 35–43, 2005.
- [37] R. Moreira, R. Alves de Sousa, R. Valente, "A solid-shell layerwise finite element for non-linear geometric and material analysis", Compos Struct, 92(6), 1517–1523, 2010.
- [38] K. Rah, W. Van Paepegem, A. Habraken, R. Alves de Sousa, R. Valente, "Evaluation of different advanced finite element concepts for detailed stress analysis of laminated composite structures", Int J Mater Form, 2(1), 943–947, 2009.
- [39] P. Liu, J. Zheng, "Recent developments on damage modeling and finite element analysis for composite laminates: A review", Mater & Design, 31(8), 3825– 3834, 2010.
- [40] I. Kreja, "A literature review on computational models for laminated composite

and sandwich panels", Cent Eur J Eng, 1(1), 59-80, 2011.

- [41] B. Svendsen, "On the representation of constitutive relations using structure tensors", Int J Engng Sci, 32, 1889–1892, 1994.
- [42] M. Bischoff, E. Ramm, "Shear deformable shell elements for large strains and rotations", Int J Numer Methods Engng, 40, 4427–4449, 1997.
- [43] P.P. Camanho, S. Bowron, F.L. Matthews, "Failure mechanisms in bolted CFRP", J Reinf Plast Compos, 17 (3), 205–233, 1998.